


**NOTES:**

1. COMPACTION AND TESTING FOR ALL AGGREGATE BASE/SUBBASE MATERIAL SHALL BE IN ACCORDANCE WITH ISPWC 802.
2. ASPHALT FOUR (4") INCHES IN THICKNESS SHALL BE PLACED IN TWO (2") INCH LIFTS. ASPHALT THREE (3") INCHES OR LESS SHALL BE PLACED IN A SINGLE LIFT.
3. GEOTEXTILE FABRIC TO EXTEND 2' MIN. BEYOND THE EDGE OF ASPHALT. ALL SEAMS TO OVERLAP 2' MIN.
4. COMPACTION AND TESTING FOR ALL HOT MIX ASPHALT SHALL BE IN ACCORDANCE WITH ISPWC SECTION 810 AND PROJECT PLANS AND SPECIFICATIONS.
5. ALL CONCRETE CURBS SHALL BE ISPWC TYPE II CURB AND GUTTER. CONCRETE MIX DESIGN TO BE CLASS 4000A WITH 3/4" AGGREGATE IN ACCORDANCE WITH ISPWC SECTION 703, CAST-IN-PLACE CONCRETE, TABLE 1. ALL OTHER CONCRETE (I.E. SIDEWALK, APPROACHES AND RAMPS) TO BE CLASS 4000B WITH 3/4" AGGREGATE IN ACCORDANCE WITH ISPWC SECTION 703, CAST-IN-PLACE CONCRETE, TABLE 1. SILANE-40 CONCRETE SEALER REQUIRED.
6. MICRO-SYNTHETIC FIBERS SHALL BE FIBERMESH OR APPROVED EQUIVALENT. LENGTH OF FIBERS SHALL BE AS RECOMMENDED BY THE MANUFACTURER. ADD 1.5 POUNDS OF FIBERMESH OR APPROVED EQUIVALENT PER CUBIC YARD OF CONCRETE, OR AS RECOMMENDED BY MANUFACTURER.
7. FOR HIGH TRAFFIC ROADS USE 4" INCHES OF HOT MIX ASPHALT, SUPERPAVE - 3, 1/2" AGGREGATE PG 64-34 OR APPROVED EQUAL AND 12" MIN. OF SUBBASE COURSE, ISPWC 2" (TYPE II) CRUSHED AGGREGATE.
8. REVEGETATE ALL DISTURBED AREAS WITH A CITY APPROVED GRASS MIXTURE OVER FOUR (4") INCHES OF TOPSOIL, PER APPROVED LANDSCAPING PLAN, OR AS INDICATED WITHIN THE PLANS.

 <b>City of McCall</b> PUBLIC WORKS	<b>PUBLIC WORKS DEPARTMENT</b> 815 N. SAMSON TRAIL McCALL, IDAHO 83638 208.634.5580	<b>CITY OF McCALL</b> <b>TYPICAL ROADWAY SECTION - LOCAL URBAN</b>			STANDARD DRAWING NO.  <b>MSD-803A</b>
		PROJECT .	DRAWN BY .	SHEET NO.	
		DATE 1/12/2023	.		1 OF 1