


**NOTES:**

1. COMPACTION AND TESTING FOR ALL AGGREGATE BASE/SUBBASE MATERIAL SHALL BE IN ACCORDANCE WITH ISPWC 802.
2. ASPHALT FOUR (4") INCHES IN THICKNESS SHALL BE PLACED IN TWO (2") INCH LIFTS. ASPHALT THREE (3") INCHES OR LESS SHALL BE PLACED IN A SINGLE LIFT.
3. GEOTEXTILE FABRIC TO EXTEND 2' MIN. BEYOND THE EDGE OF ASPHALT. ALL SEAMS TO OVERLAP 2' MIN.
4. COMPACTION AND TESTING FOR ALL HOT MIX ASPHALT SHALL BE IN ACCORDANCE WITH ISPWC SECTION 810 AND PROJECT PLANS AND SPECIFICATIONS.
5. REVEGETATE ALL DISTURBED AREAS WITH A CITY APPROVED GRASS MIXTURE OVER FOUR (4") INCHES OF TOPSOIL, PER APPROVED LANDSCAPING PLAN, OR AS INDICATED WITHIN THE PLANS.
6. FOR HIGH TRAFFIC ROADS USE 4" INCHES OF HOT MIX ASPHALT, SUPERPAVE – 3, 1/2" AGGREGATE PG 64-34 OR APPROVED EQUAL AND 12" MIN. OF SUBBASE COURSE, ISPWC 2" (TYPE II) CRUSHED AGGREGATE.

 <b>City of McCall</b> <small>PUBLIC WORKS</small>	<b>PUBLIC WORKS DEPARTMENT</b> 815 N. SAMSON TRAIL McCALL, IDAHO 83638 208.634.5580	<b>CITY OF McCALL</b>		STANDARD DRAWING NO.  <b>MSD-803B</b>
		TYPICAL ROADWAY SECTION - LOCAL RURAL		
		PROJECT	DRAWN BY	SHEET NO.
		DATE	1/12/2023	1 OF 1